


2f to 24f 3.0mm Micro Internal LSZH Cable

LinkPro CABLE CONSTRUCTIONS

Description

The cable uses 250μm OM1, OM2, OM3, OM4, OM5 multimode or ITU-T G.652.D, ITU-T G.657.A1 and ITU-T G.657.A2 single mode Optical fibers as optical transmission medium, covered with aramid yarns strength member in a Low Smoke Zero Halogen (LSZH) Jacket.



Features

- High-integrated colored bare fiber design
- Aramid yarns providing excellent tensile performance
- Anti-corrosion, flame-retardant and environment-friendly

Applications

- Ideal for internal inter-connect using MPO or MTP connectivity
- Specialist cable for high density connectivity including data centers
- Interconnection between instruments and communication equipment

Optical Fiber Characteristic

Fiber Type	After cabled max attenuation(dB/km)				Overfilled modal bandwidth(OFL)	Effective modal bandwidth	Minimum bending radius
	1310nm	1550nm	850nm	1300nm	850/1300nm (MHZ.km)	850/953nm (MHZ.km)	mm
G.652.D	0.4	0.3	-	-	-	-	16
G.657.A1	0.4	0.3	-	-	-	-	10
G.657.A2	0.4	0.3	-	-	-	-	7.5
G.657.B3	0.4	0.3	-	-	-	-	5
OM1	-	-	3.5	1.5	≥200/500	-	37.5
OM2	-	-	3.5	1.5	≥500/500	-	7.5
OM3	-	-	3.5	1.5	≥1500/500	≥2000	7.5
OM4	-	-	3.5	1.5	≥3500/500	≥4700	7.5
OM5	-	-	3.5	1.5	≥3500/500	≥4700/2470	7.5

Fiber Identification (IEC TR 63194)

1	2	3	4	5	6	7	8	9	10	11	12
Blue	Orange	Green	Brown	Gray	White	Red	Black	Yellow	Purple	Pink	Aqua
13	14	15	16	17	18	19	20	21	22	23	24
Blue+b	Orange+b	Green+b	Brown+b	Gray+b	White+b	Red+b	Natural+b	Yellow+b	Purple+b	Pink+b	Aqua+b

Note: +b = buffer with a black band ring mark

Constructions and Technical Parameters

Items		Descriptions
Fiber counts		2~24
Outer sheath	Material	LSZH
	Color	TBD
	Strength member	Aramid yarns
	Diameter(mm) approx.	3.0 ± 0.1
Minimum bending radius	Static	10×Cable diameter
	Dynamic	20×Cable diameter
Plywood drum Dimensions(mm) approx.(Flange, Barrel, Width)		F400, B200, W330
Cable weight(kg/km) approx.		7.0

Mechanical and Environmental Characteristics

Items	Descriptions		Test Method	Requirements
Tensile performance	Short-term	220N	IEC 60794-1-21 Method E1	IEC 60794-2-20
	Long-term	66N		
Crush resistance	Short-term	350N/10cm	IEC 60794-1-21 Method E3	IEC 60794-2-20
Temperature range	-20 °C to +70 °C		IEC 60794-1-22 Method F1	IEC 60794-2-20
Other parameters: according to IEC 60794-2-20 and IEC 60794-1-21				

Environmental Temperature

Items	Value
Installation temperature	-10 °C to +60 °C
Operation temperature	-20 °C to +70 °C
Storage temperature	-40 °C to +70 °C

Fire Performance

Fire Test Description	Fire Test Specification	Requirement
Smoke emission	IEC 61034-1 & 2	60% transmittance
Vertical Flame Propagation	IEC 60332-1-2	PASS
Toxicity (Halogen free)	IEC 60754-1	PASS
Acid gas emission	IEC 60754-2	Conductivity<10us/mm and pH > 4,3

Identification

Unless otherwise specified, the cable sheath marking shall be as follows:

OPTICAL CABLE D/125 AAA ##F LSZH YYWWD xxxxM *****

- Ink Color: Black
- D/125: is the optical fiber core size where OM1 will be printed 62.5/125, OM2, OM3, OM4, OM5 will be printed 50/125. ITU-T G.657.A1, G.657.A2 will be printed 9/125
- AAA: is the fiber Type OM1, OM2, OM3, OM4, OM5, G.652.D, G.657.A1 or G.657.A2
- ##F: is the optical fiber count 2, 4, 8, 12, 16, or 24
- YYWWD: Year + Week + Day
- xxxxM: Sequential meter marking, Interval: 1m
- *****: Cable Reel No., Per Manufacturer or owner

Jacket Color(Pantone Color)

Blue	Orange	Green	Brown	Gray	White	Red	Black
PT 3005U	PT 1505U	PT 347U	PT 483U	PT 431U	RAL 9003	PT 206U	RAL 9005
Yellow	Purple	Pink	Auqa	Light Green	Lime Green	Erika Violet	
PT 107U	PT 267U	PT 707U	PT 3245U	PT 361U	PT 381U	RAL 4003	

Packing

Plywood drums protection. During transportation, right tools should be used to avoid damaging the package and to handle with ease. Cables should be protected from moisture; kept away from high temperature and fire sparks; protected from over bending and crushing; protected from mechanical stress and damage.

Delivery Length

Standard delivery length is 2km/drum. Other lengths available upon agreement.

Chemical Characteristics

Free of hazardous substances according to RoHS 2011/65/EU